



WIDE FORMAT INKJET SILVER GLOSS FILM



Metalized polyester film optimized for latex, solvent and eco-solvent inkjet print applications and compatible with UV-cured inks.

- High gloss mirror finish
- Maximum impact for point of sale and other advertising, packaging, mock-ups, labels, boxwraps
- The first water resistant digital solution for mirror graphics
- Antistatic reverse

SILVER GLOSS FILM

WEIGHT CALIPER/GSM	MICRONS	LINER	WIDTH INCHES	WIDTH MM	LINEAL FEET	CORE	CODE NUMBER
5.0/163	119	-	24	610	13	3	67-82214
	119	-	50	1270	100	3	82204
	119	-	60	1524	100	3	82213

Visit mohawkconnects.com for more complete stocking info.

COMPATIBILITY

SOLVENT/ ECO SOLVENT	LATEX	UV CURED
✓✓✓	✓✓	✓✓✓

- ✓✓✓ *Excellent*
- ✓✓ *Good*
- ✓ *Fair*
- ✗ *Not Compatible*

SILVER GLOSS FILM

TYPICAL PERFORMANCE VALUES

The following information on physical and chemical characteristics is based upon tests believed to be reliable. The values are intended only as a source of information. They are given without guarantee and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of this material or his/her specific purpose. (Data represents averages and is not intended for use as a specification.)

Ink dry time: rapid drying depending upon type and amount of ink, relative humidity and temperature

Chemical resistance: not designed to be chemical resistant

Handling requirements: due to absorptive nature of the coating, avoid touching the coated surface with bare skin. Always wear chemical resistant gloves when handling inkjet-coated materials. Rolls are supplied with the coated surface wound out.

Durability outdoor: not designed for permanent outdoor use

Solvent resistance: not designed to be solvent resistant

Printing temperature: 59 - 86°F / 30 - 65%RH

Display use: -40 - 176°F / 10 - 90%RH

Ideal storage conditions: 50 - 68°F / 20 - 50%RH

Shelf life: two years at ideal storage conditions, stored in original packaging

PHYSICAL CHARACTERISTICS

PROPERTY	TYPICAL VALUE	UNIT	TEST METHOD
Total Thickness	5 +/- 0.2	Mil	Electronic micrometer
Weight	163 +/- 4	G/m ²	Internal method
Tensile Strength	MD 17 TD 10	KfG / mm ²	ASTM D882-83
Melting Point	482	°F	ASTM E794-85

CAUTION

Users should make their own assesment as solvent inks can vary widely. This is more dependent on ink manufacturer and type than it is on the printing hardware.

For more information contact your paper merchant or Mohawk Digital Specialist.

©2016 Mohawk Fine Paper Inc., Mohawk®, and the corporate logo are registered trademarks of Mohawk.

All statements, technical information and recommendations about Mohawk products are based upon tests beblieved to be reliable but do not constitute a guarantee or warranty. The purchaser must independently determine the suitability of this product for its purposes. See Mohawk Electronic Printing Guarantee for further details.

July 2017